## **READY-MIXED, ALUMINUM PAINT**

PRODUCT NUMBER 103

**TYPE** The paint based on special artificial resin, dry oil and aluminum paste.

**USES** Used for steel structures, street lamps and exterior of storage tanks.

**CHARACTERISTICS** 1. Metal-like appearance.

2. Tough and hard film with good adhesion.

3. Good weather resistance and color retention.

4. Scales-like paint film, excellent resistance to moisture and water.

5. Easy Application.

Silver **COLOR** 

Above 20 m<sup>2</sup>/L HIDING POWER Above 0.95 Kg/L MASS DENSITY 55~75 KU (25°C) VISCOSITY

Set-to-touch Dry hard 8 hrs. (25°C) 1hr. **DRYING TIME** 

**OPTIMUM FILM THICKNESS** Wet 70 microns Dry 25 microns  $15.0 \text{ m}^2/\text{Kg}$ 54.0 m³/Gal 14.3 m<sup>2</sup>/L THEORETICAL COVERAGE

**OVERCOATING INTERVALS** Min. 10 hrs. (25°C)

Above 45% NON-VOLATILE CONTENT

Continuous 80 ℃ Intermittent 120 °C **HEAT RESISTANCE** 

No.805 Paint Thinner (OM-07) **THINNER** THINNING RATE 5~10% (depends on tools used)

No.992 Aluminum Tripolyphosphate Primer PRECEDING COATS

No.905 \ 906 Red Lead Primer (OP-91/OP-92)

No.911 Red Oxide Primer (SP-70) No.907 Zinc Chromate Primer (OP-93)

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Spray, Brush, Roller. NOTE

1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.

- 2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.
- 3. Avoid applying the paint in rainy, humid weather or substrate temperature excessively high to  $40^{\circ}$ C or low to  $10^{\circ}$ C.
- 4. Avoid applying to insufficient drying of previous paint coat.
- 5. Wash the brush tool by No.805 before use to prevent have the darken paint film.

EPDM010103XX V1.0

## YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443