## RAINBOW

## WATER-BASED EPOXY CLEAR PRIMER/SEALER

No.1030CP **PRODUCT NUMBER** Two pack type clear primer based on water-borne epoxy binder and TYPE special hardener. The primer is suitable for cement wall, cement products, cement borad, USES plasterboard, and conrete wall etc. **CHARACTERISTICS** 1. Excellent resistance to water and alkali. 2. Hard film and good adhesion. 3. Excellent compatibility with epoxy and PU topcoat. Yellowish clear COLOR Above 0.9 kg/L (Mixer) S.G. 50~65 KU (Mixer) (25 ) VISCOSITY (25 ) Set-to-touch 4 hrs. Dry hard 12 hrs. Full Cured 7 days **DRYING TIME (25** ) Wet  $40 \mu$  (microns) Dry  $15\mu$  (microns) **OPTIMUM FILM THICKNESS** Min. 14 hrs. (25 ) OVERCOATING INTERVALS (25) 24.6 m<sup>2</sup>/L 90.0 m<sup>2</sup>/Gal THEORETICAL COVERAGE Base : hardener. = 25 : 75 MIXER RATE Above 35% (Mixer) NON-VOLATILE CONTENT 1.25 hrs. (Mixer, 25 ) POT LIFE Water THINNER 0~5% (Excluded cleaning tools) THINNING RATE Minimum 1 year under normal storage conditions. STORAGE SHELF LIFE Air-spray, Brush. APPLICATION METHOD NOTE 1. Mix base and hardener according to the mixing ratio and stir thoroughly. 2. Adhered moisture, grease, and dirt on substrate must be cleaned thoroughly. 3. Avoid applying the paint in rainy weather or humidity above 85% RH, particularly, a wet surface must be thoroughly dried.

4. All tools must be cleaned immediately after use.

## YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN TEL: 886-7-8713181 FAX: 886-7-8715443