



# RAINBOW

## BAKING ENAMEL

PRODUCT NUMBER	1101 / 1102 / 1104 / 1117 / 1119
TYPE	The low temperature baking enamel based on short-oil alkyd resin and melamine resin with weather resistant pigment.
USES	Used for vehicles, agricultural machineries, electronic ware, steel furniture and general tools etc.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Tough film and smooth appearance.</li><li>2. Excellent adhesion and abrasion resistance.</li><li>3. Excellent weather resistance and gloss and color retention.</li><li>4. Excellent resistance to oils and solvents.</li><li>5. Excellent resistance to water and chemicals such as salts, acids, alkalis etc.</li></ol>
GLOSS	Above 90%      No. 1119 : flat
COLOR	Desired colors
HIDING POWER	Above 8.0 m <sup>2</sup> /L ( depending on colors )
MASS DENSITY	Above 0.9 Kg/L
HARDNESS	Above 26 ( Sward )
CROSS-CUT TEST	Adhesive rate 100/100 based on sample piece of one square millimeter scratch
IMPACT RESISTANCE STRENGTH	φ 12.5 mm × 0.3 kg × 50 cm × 0.8 mm steel : no cracks
VISCOSITY	65~75 KU (25°C)
DRYING TIME	Dry hard 30 minutes ( 120°C )
FILM THICKNESS	Wet 90 microns      Dry 25 microns
THEORETICAL COVERAGE	42.0 m <sup>2</sup> /Gal      11.1 m <sup>2</sup> /L      12.3 m <sup>2</sup> /Kg
VOLUME SOLIDS	Above 28%
THINNER	No.1112 Baking Enamel Thinner ( or Xylene )
THINNING RATE	20~30% ( Cleaning tools excluded )
SUBSEQUENT COATING	No.1106 Baking Varnish
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Spray, Electrostatic spray.
NOTE	<ol style="list-style-type: none"><li>1. Use specified thinner to dilute the paint to reach standard spraying viscosity ( Ford cup #4 ) 16± 2 seconds.</li><li>2. Adhered moisture, grease and dust on the substrate must be cleaned thoroughly.</li><li>3. After applying, keep static about 10~15 minutes in room temperature, until the solvent within paint film vaporizes thoroughly, and then baking in accordance with baking temperature and time. ( Standard baking temperature and time : 120± 5°C , 30 minutes )</li></ol>

EPDM111117XX V1.0

# YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.  
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181  
FAX:886-7-8715443