

\_ . . . \_ \_ . .. .. .\_ \_



## **HEAT-RESISTING PAINT, 500**

| PRODUCT NUMBER              |
|-----------------------------|
| TYPE                        |
| USES                        |
|                             |
| CHARACTERISTICS             |
|                             |
|                             |
|                             |
| COLOR                       |
| HIDING POWER                |
| WEIGHT                      |
| VISCOSITY (25 )             |
| DRYING TIME (25 )           |
| OPTIMUM FILM THICKNESS      |
| THEORETICAL COVERAGE        |
| OVERCOATING INTERVALS (25 ) |
| NON-VOLATILE CONTENT        |
| THINNER                     |
| THINNER RATE                |
| SUBSEQUENT COATS            |
| STORAGE SHELF LIFE          |
| APPLICATION METHOD          |
| NOTE                        |

No.1502/1503 Heat-resisting paint based on silicone resin with heat-resisting pigments. Heat-resisting paint for generators, boilers, chimneys and other high temperature facilities in chemical and steel works. 1. Good high heat resistance withstands it up to 500 . 2. Excellent resistance to water and oil. 3. Good adhesion. 4. Easy application. No.1503 :Black No.1502 :Silver Above 12.5 m<sup>2</sup>/L Above 1.0 kg/L 50~70 KU (25 ) Set-to-touch 60 mins. (25) Dry hard 1 mins. (200 Wet 50 µ (microns) 15µ (microns) Dry 75.5 m²/Gal 20.0 m<sup>2</sup>/L  $20.0 \text{ m}^2/\text{kg}$ Min. 6 hrs. 30 % No.1521 5~15% (depends on tools used) No.1501 500 Minimum 1 year under normal storage conditions. Spray, Brush 1. Moisture, greases, sludge, old paint and rust must be thoroughly removed from substrate, preferably sand blast to the standard above SIS Sa 2. 2. Principally, paint application should be conducted at ambient temperature,

- blistering and scaling are apt to occur when substrate temperature exceeds 60 .
- Primer and topcoat should be limited to two even coats each, but the total dry film thickness must be kept below 80 microns; otherwise, cracking and scaling would occur.
- 4. After completion of painting, slowly heat up to half of service temperature and keep it for one hour, and then raise to service temperature. Directly heating up to maximum service temperature would surely induce blistering or scaling.

## YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN TEL: 886-7-8713181 FAX: 886-7-8715443