POLYURETHANE COATING, WHITE (N-TYPE)

PRODUCT NUMBER 725

CHARACTERISTICS

TYPE A two-pack, non-yellowing polyurethane coating based on acrylic resin, polyol resin and

isocyanate hardener with weather resistant titanium dioxide.

USES Used for wood products, vehicle, metal products and FRP.

1. High gloss and hardness, good gloss and color retention.

2. Excellent adhesion and abrasion.

3. Excellent resistance to acids, alkalis, oils and salts.

4. High gloss with smooth appearance.

FINISH High gloss COLOR White

HIDING POWER Above 12.5 m²/L (mixture) MASS DENSITY Above 1.1 Kg/L (mixture) 60~80 KU (mixture, 25°C) VISCOSITY

DRYING TIME Dry hard 6 hrs. (25°C). Set-to-touch 1 hr.

OPTIMUM FILM THICKNESS Wet 60 microns Dry 30 microns $16.7 \text{ m}^2/\text{L}$ 15.2 m²/Kg THEORETICAL COVERAGE 63.0 m³/Gal

Max. 6 months **OVERCOATING INTERVALS** Min. 4 hrs.

MIXING RATIO Base: hardener = 87:13 (by wt.)

NON-VOLATILE CONTENTS Above 60% (mixture) **POT LIFE** 4 hrs. (mixture, 25°C)

HEAT RESISTANCE Continuous 93°C Intermittent 121°C

THINNER No.736 Polyurethane Thinner THINNING RATE 10~25% (cleaning tools excluded) PRECEDING COATS No.711 Polyurethane Sanding

No.733 Polyurethane Zinc Chromate Primer (for metal)

Epoxy Primers Series

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

Spray, Brush, Roller

1. Mix base and hardener according to the mixing ratio and stir thoroughly.

2. Adhered moisture, grease, dust on substrate must be removed thoroughly.

3. Please use special thinner for dilution to avoid causing bubbles or pinholes.

4. Hardener cover must be tightly closed to avoid reaction with moisture in air to form bubbles and gelation.

5. Mixture of base and hardener must be used up within pot life.

6. Strictly controlling application, not to exceed 50 microns per coat, to avoid bubbles formation.

7. All equipments must be cleaned immediately after use.

8. The lacquer sanding is not suitable as a primer for this paint.

Avoid applying paint in rainy or the moisture above 85% RH, otherwise the adhesion will be affected by moisture of substrate and the paint film will be loss its gloss.

EPDM710725XX V1.3

APPLICATION METHOD

NOTE

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443