## **RAINBOKYD 15**

PRODUCT NUMBER 30015

**TYPE** General purpose gloss paint based on a modified alkyd resin.

**CHARACTERISTICS** 1. Good appearance and gloss retention..

2. Good abrasion and weather resistance.

3. Good adhesion to oleoresinous and chlorinated rubber primers

4. Good resistance to oil and water

5. Easy application

6. Low-flame spread

**GLOSS** Gloss

**COLORS** White and various other colours. **VOLATILE ORGANIC** VOC 450 (g/l) below

COMPOUND CONTENT

PRODUCT WEIGHT Above 1.0 kg/L

Set-to-touch 2 hrs Dry hard 15 hrs  $(25^{\circ}C)$   $(35\mu)$ **DRYING TIME** 

OPTIMUM FILM THICKNESS Wet 80µ (Micron) Dry 35 µ (Micron)

45 ±2% **VOLUME SOLID** 

47.3 m³/Gal 12.5 m<sup>2</sup>/L THEORETICAL COVERAGE

**OVERCOATING TABLE** 24 hours or more

No.805 Paint Thinner (OM-07) **THINNER** 

THINNER RATE  $0 \sim 2\%$  (by bush and roller)  $0 \sim 3\%$  (Airless)

RECOMMENDED SPEC. Please refer the painting specification

SHELF LIFE Minimum two years under normal storage condition

APPLICATION METHOD Airless spray, Bush and Roller

NOTE 1. Adhered water, grease and dust on substrate must be thoroughly clean.

> 2. Substrate temperature should be 3<sup>°</sup>C above dew point, rainy day and relative humidity during application and curing should be below 85%, or job is to be stopped.

3. Whilst application in the confine space, adequate ventilation must be maintenance.

EPDM3030015X V1.0